

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 61-219534

(43)Date of publication of application : 29.09.1986

(51)Int.Cl.

B23P 11/02  
// C04B 37/02

(21)Application number : 60-058855

(71)Applicant : SHIN MEIWA IND.CO LTD

(22)Date of filing : 22.03.1985



(72)Inventor : YAMANE KENJI

## (54) COMPOSITE MATERIAL OF CERAMIC AND METAL

### (57)Abstract:

**PURPOSE:** To produce a low-cost composite material, by a method wherein a ceramic base material is shrink-fit in the fastening part of a ceramic member, consisting of a metallic base material, which is low cost and easy to machine, through a metal having the low coefficient of expansion.

**CONSTITUTION:** A pure titanium ring 3 is shrink-fit in an alloy 1 made of stainless at about 220°C (as shown in fig. A). Thereafter, the titanium part is cut (as shown in fig. B), and a seal ring 2 made of ceramic is shrink-fit in the titanium part at about 220°C. In which case, fastening allowance of ceramic is about 0.04mm, and even if ceramic is cooled to a room temperature, it is prevented from break. Further, even if it is heated to 180°C, the pure titanium ring and the seal ring are prevented from separation. Thus, only a fastened part during shrink-fit of the metallic base material 1 forms a metal 3 which is difficult to machine and has the low coefficient of expansion, and other part forms a metal which is low cost and easy to machine, and this provides a low cost composite material in terms of both a material cost and easiness in machining.



## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of

rejection]

[Date of requesting appeal against examiner's  
decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2000 Japan Patent Office